

Replaces:
RN 810-3-1:2023-04-26

Delivery Conditions for case-hardening steel

**Punched discs and rings of 18CrNiMo7-6
for rotors with peripheral speeds <50 m/s**

| Contents | Page |
|---------------------------------|------|
| 1 Scope | 2 |
| 2 References | 2 |
| 3 Chemical composition | 3 |
| 4 Physical characteristics..... | 3 |
| 5 Manufacturing..... | 3 |
| 6 Other requirements..... | 4 |

Changes

2025-01-22:

The following changed in comparison to RN 810-3-1:2023-04-26:

- a) updated references
- b) ultrasonic testing outsourced in RN 1934
- c) chapter 6 a): correction regarding the authorisation of IACS member societies
- d) chapter 6 f): wording for required certificates clarified
- e) editorially revised

| | | | | |
|-----------------------------|----------------------|--------------------------------|------------------------------------|----------------|
| Responsible division: EK | Editor: M. Förste | Approval: see doc. workflow | Technical reference: C. Eschert | Page: 1 / 4 |
|-----------------------------|----------------------|--------------------------------|------------------------------------|----------------|

1 Scope

| | | |
|----------------------------------|-----------------------|---|
| This factory standard applies to | Material-No.: | 1.6587 |
| | Material designation: | 18CrNiMo7-6 |
| | Delivery conditions: | Punched disc, Ring hot formed; unmachined / pre-turned |
| | Use case: | Rotors with peripheral speeds < 50 m/s |

2 References

The following documents, cited in part or in whole, shall apply for the use of this standard. In case of dated references, only the referenced edition applies; in case of undated references, the latest edition of the referenced document (including all amendments) applies. The applicable version of the standards listed below shall apply to all contents not covered by this factory standard.

| | |
|-------------------|--|
| DIN 50125 | Testing of metallic materials - Tensile test pieces |
| DIN 50602:1985-09 | Metallographic examination; microscopic examination of special steels using standard diagrams to assess the content of non-metallic inclusions |
| DIN EN 10021 | General technical delivery conditions for steel products |
| DIN EN 10204 | Metallic products - Types of inspection documents |
| DIN EN ISO 148-1 | Metallic materials - Charpy pendulum impact test - Part 1: Test method |
| DIN EN ISO 642 | Steel - Hardenability test by end quenching (Jominy test) |
| DIN EN ISO 643 | Steels - Micrographic determination of the apparent grain size |
| DIN EN ISO 683-3 | Heat-treatable steels, alloy steels and free-cutting steels - Part 3: Case-hardening steels |
| RN 1089 | Rings; Machining allowances and tolerances |
| RN 1092 | Punched discs; Machining allowances and tolerances |
| RN 1550 | Material samples |
| RN 1567 | Remanent magnetism in components |
| RN 1934 | Test instruction; Ultrasonic testing |
| RN 1936 | Labelling; Raw material, parts and gearboxes |

3 Chemical composition

Table 1 Chemical composition in %

| | C | Si | Mn | P | S | Cr | Mo | Ni | V | Cu |
|-----|------|------|-------|-------|-------|------|----------------|--------|----------------|--------|
| min | 0.15 | | 0.50 | | | 1.50 | 0.25 | 1.40 | | |
| max | 0.21 | 0.40 | 0.90 | 0.025 | 0.010 | 1.80 | 0.35 | 1.70 | | 0.30 |
| | Sn | Al | N | Ti | Nb | Sb | O ₂ | Ca | H ₂ | Al / N |
| min | | 0.02 | 0.008 | | | | | | | |
| max | | 0.05 | 0.015 | 0.006 | | | 25 ppm | 0.0015 | 2.0 ppm | 4.0 |

4 Physical characteristics

Table 2 Mechanical properties

(Test temperature: 20 °C)

| | Rm | Rp _{0.2} | A5 [%] | | | Z [%] | | | Av [J] | | |
|---------------|----------------------|----------------------|---------|-------|--------|---------|-------|--------|---------|-------|--------|
| | [N/mm ²] | [N/mm ²] | length. | tang. | cross. | length. | tang. | cross. | length. | tang. | cross. |
| | min | min | min | min | min | min | min | min | min | min | min |
| rings | 1080 | 785 | -- | 10 | 8 | -- | 35 | 25 | -- | 35 | 25 |
| punched discs | 1080 | 785 | 12 | 10 | 8 | 45 | 35 | 25 | 45 | 35 | 25 |

Note: The final mechanical properties can only be achieved after heat treatment (case hardening or quenching and tempering), which is usually carried out at REINTJES. When delivered, the material has lower strengths (see chapter 5 c).

- a) Structure, inclusions
- grain size, standard: DIN EN ISO 643
 - purity degree, standard: DIN 50602
- standard series: Table C.1; G ≥ 5
method: K; K4 ≤ 20
- b) Hardenability
- standard: DIN EN ISO 683-3
 - testing: DIN EN ISO 642
 - end distance [mm]: 5 11 25 40
 - hardness [HRC]: 42-48 40-47 35-43 33-41
- scatter band: +HH
- c) Additional properties
- radioactivity: ≤ 0.10 Bq/g

5 Manufacturing

- a) Casting method and forging reduction ratio (VG)
- continuous casting: VG ≥ 5.0
 - ingot casting: VG ≥ 3.0
- b) Melting
- making process: E, LD, ESU (on special request)
 - post-treatment: vacuum degassing (VD) for E or LD
- c) Heat treatment
- treatment condition: Ø Da < 1000: +FP / +QT Ø Da ≥ 1000: +QT
 - treatment method: liquid quenching and tempering
 - anneal to: 600 to 850 N/mm² tensile strength
- d) Surface condition
- defect depth: ≤ machining allowance
 - unmachined: crack and scale free
 - repair by welding: only after approval by REINTJES
 - pre-turned (on request): Ra 6.3 (max. Rz 63)
- e) Manufacturing tolerances: RN 1089 and RN 1092

6 Other requirements

- a) Steel and forging plant
 - certified acc. to [DIN EN ISO 9001 ff.](#)
 - approved by at least one member society of IACS

- b) Testing
 - material identification check: [to be carried out](#)
 - ultrasonic testing: [RN 1934 for rotors with peripheral speeds < 50 m/s](#)

- c) Sample material and collection
 - [RN 1550](#)

- d) Remanent magnetism
 - [RN 1567](#)

- e) Labelling
 - [RN 1936](#)

- f) Documentation (must be digitally available upon delivery)
 - acceptance test certificate 3.1 acc. to DIN EN 10204 per melt and furnace trip or per piece or production lot with specification of primary material and forging ratio
 - copy of the acceptance test certificate 3.1 from the steel manufacturer
 - evidence of radioactivity and remanent magnetism
 - forging schedule (on special request)