

Replaces: RN 840-1-2:2023-04-06

# **Delivery Conditions for quenched and tempered steel**

# Steel bars of 34CrNiMo6 for rotors with peripheral speeds > 50 m/s

Content			
1	Scope	2	
2	References	2	
3	Chemical composition	3	
4	Physical characteristics	3	
5	Manufacturing	4	
6	Other requirements	1	

## Changes

#### 2025-01-22:

The following changed in comparison to RN 840-1-2:2023-04-06:

- a) updated references
- b) ultrasonic testing outsourced in RN 1934
- c) chapter 6 a): correction regarding the authorisation of IACS member societies
- d) chapter 6 g): wording for required certificates clarified
- e) editorially revised

Responsible division:	Editor	Approval:	Technical reference:	Page:
EK	M. Förste	see doc. workflow	C. Eschert	1/4



### 1 Scope

This factory standard applies to Material no.: 1.6582

Material designation: 34CrNiMo6

Delivery conditions: Steel bar; free-form forged

hot formed; pre-turned

Use case: Rotors with peripheral speeds > 50 m/s

#### 2 References

The following documents, cited in part or in whole, shall apply for the use of this standard. In case of dated references, only the referenced edition applies; in case of undated references, the latest edition of the referenced document (including all amendments) applies. The applicable version of the standards listed below shall apply to all contents not covered by this factory standard.

DIN 7527-6:1975-02 Steel Forgings; Machining Allowances and Permissible Variations for Open-die

**Forged Bars** 

DIN 50602:1985-09 Metallographic examination; microscopic examination of special steels using

standard diagrams to assess the content of non-metallic inclusions

DIN EN 10021 General technical delivery conditions for steel products

DIN EN 10204 Metallic products - Types of inspection documents

DIN EN ISO 642 Steel - Hardenability test by end quenching (Jominy test)

DIN EN ISO 643 Steels - Micrographic determination of the apparent grain size

DIN EN ISO 683-2 Heat-treatable steels, alloy steels and free-cutting steels - Part 2: Alloy steels for

quenching and tempering

RN 1550 Material samples

RN 1567 Remanent magnetism in components

RN 1934 Test instruction; Ultrasonic testing

RN 1936 Labelling; Raw material, parts and gearboxes



## 3 Chemical composition

Table 1 Chemical composition in %

	С	Si	Mn	P	S	Cr	Мо	Ni	V	Cu
min.	0.30		0.50			1.30	0.15	1.30		
max.	0.38	0.40	0.80	0.015	0.005	1.70	0.30	1.70		0.30
	Sn	Al	N	Ti	Nb	Sb	O <sub>2</sub>	Ca	H <sub>2</sub>	Al/N
min.		0.01								
max.	0.05	0.04	0.012	0.05			20 ppm	0.0030	1.7 ppm	3.7

# 4 Physical characteristics

**Table 2** Mechanical properties (Test temperature:  $20^{\circ}$  C / degree of transformation:  $\phi \ge 6.0$ )

Diameter		Rm	Rp <sub>0.2</sub>	A5 [%]		Z [%]		Av [J]	
[mm]		[N/mm²]	[N/mm²]	longit.	transv.	logit.	transv.	longit.	transv.
over	up to	min.	min.	min.	min.	min.	min.	min.	min.
	40	1100	900	11	-	35	-	30	-
40	100	1000	800	13	-	40	-	35	-
100	160	950	700	14	13	40	34	45	22
160	250	900	650	14	13	40	34	45	22
250	500	850	600	15	13	50	45	45	22
500	750	800	550	13	11	55	35	45	30
750	1000	750	500	13	11	50	35	45	30

a) Structure, inclusions

grain size, standard: DIN EN ISO 643 standard series: Table C.1; G ≥ 6
 purity degree, standard: DIN 50602 method: K; K4 ≤ 20

b) Hardenability

• Standard: DIN EN ISO 683-2 scatter band: +HH

• testing: DIN EN ISO 642

end distance [mm]: <u>5</u> <u>11</u> <u>25</u> <u>40</u> hardness [HRC]: 53-58 51-57 50-57

c) Additional properties

• radioactivity:  $\leq 0.10 \text{ Bq/g}$ 



# 5 Manufacturing

a)	Casting method:	ingot casting				
b)	Melting					
	<ul><li>making process:</li></ul>	E, LD, ESU (on special request)				
	<ul><li>post-treatment:</li></ul>	vacuum degassing (VD) for E or LD				
c)	Heat treatment					
	<ul> <li>treatment condition:</li> </ul>	+QT, quenched and tempered, stress-relieved annealed after pre-machining				
	• treatment method:	liquid quenching and tempering				
d) Surface condition						
	<ul><li>defect depth:</li></ul>	≤ machining allowance				
	<ul><li>unmachined:</li></ul>	rust-, crack- and scale-free pre-turned: max. Rz 40				
	<ul><li>repair by welding:</li></ul>	not permitted				
e)	Manufacturing tolerances:	DIN 7527-6				

## **6** Other requirements

a)	Steel and forging plant								
	<ul> <li>certified acc. to</li> </ul>	DIN EN ISO 9001 ff.							
	<ul> <li>approved by at least one member</li> </ul>	per society of IACS							
b)	Delivery condition								
	<ul><li>bar length:</li></ul>	5 - 6 m	rod end:	smooth sawn					
	<ul><li>bar weight:</li></ul>	≤ 10 t							
c)	Testing								
	<ul> <li>material identification check:</li> </ul>	to be carried out							
	<ul><li>ultrasonic testing:</li></ul>	RN 1934 for rotors with peripheral speeds > 50 m/s							
d)	Sample material and collection								
	•	RN 1550							
e)	Remanent magnetism								
	•	RN 1567							
f)	Labelling	_	_						
	•	RN 1936							

- g) Documentation (must be digitally available upon delivery)
  - acceptance test certificate 3.1 acc. to DIN EN 10204 per melt and furnace trip or per piece or production lot with specification of primary material and forging ratio
  - copy of the acceptance test certificate 3.1 from the steel manufacturer
  - evidence of radioactivity and remanent magnetism
  - forging schedule (on special request)